

Shoe Upper Tapes

Product Code	Adhesive system	Backing Material	Total Thickness (mm)	Tensile Strength (kg/cm)	Elongation (%)	Adhesion to steel (gms/cm)
Cotton Reinforcement Tapes						
F-240	Rubber	Cotton Fabric-White/Black	0.27	6	10	200
F-242	Rubber	Cotton Fabric-White with Liner	0.2	6	10	200
F-243	Rubber	Cotton Fabric-Black with Liner	0.22	6	10	200
Back Seam Tapes						
F-250	Rubber	Masking Paper	0.14	2	10	200
F-253	Rubber	Non-Woven Spun Bonded	0.42	5	30	250
F-ETK	Rubber	Non-Woven Spun Bonded	0.5	7.5	30	200
F-856	Rubber	Knitted Fabric - Black	0.40	3	30	200
F-857	Rubber	Knitted Fabric - White	0.35	3	30	200
F-856/857 SE	Rubber	Serrated Knitted Fabric - Black/White- 15 and 20mm	0.35	3	25	200
Reinforcement Tapes						
F-802	Rubber	Thin Polyester Fabric - Black/White	0.12	10	20	200
F-803	Rubber	Polyester Fabric - Black/White	0.15	16	35	200
F-258	Rubber	Thin Nylon Fabric - White	0.13	10	30	200
F-259	Rubber	Special Nylon Fabric - White	0.22	22	35	200
F-260	Rubber	Nylon Fabric - White	0.17	16	35	200
F-262	Rubber	Nylon Fabric-White with Liner	0.18	16	35	200
F-263	Rubber	Special Nylon Fabric-White with Liner	0.22	22	35	200
F-269	Rubber	Special Nylon Fabric - Black	0.22	22	35	200
F-270	Rubber	Nylon Fabric - Black	0.17	16	35	200
F-272	Rubber	Nylon Fabric - Black with Liner	0.18	16	35	200
Topline Tapes						
F-280	Rubber	Polyester / Rayon Fabric	0.4	40	30	
Double Sided tapes						
F-408	Rubber	Fabric coated on one side with Pressure Sensitive Adhesive and on another side with a Heat Activated adhesive in White and Black. Supplied with a liner.	0.15	10	30	200
F-409	Hot melt Rubber	Tissue Paper	0.085	0.85	1	400
F-444	Solvent Acrylic	Tissue Paper with Aggressive Adhesive, suitable for different types of leather. Can withstand high temperature	0.10	1.5	3	400
F-422	Hot melt Rubber	Polyester Fabric- White/Black	0.16	10	20	250
F-457	Hot melt Rubber	Economy Grade Tissue Paper	0.085	0.85	1	400
F-458	Acrylic	Tissue Paper -Economy Grade	0.09	0.50	5	400

Note: All statements, Technical Information and Recommendations are based on Test, we believe to be reliable and should not be taken to frame specifications. Before using the Tape the user shall determine the suitability of the product for his intended use.