

Bangkok Synthetics Co.,Ltd

175 Sathorn City Tower 22nd Fl., South Sathorn Road, Tungmahamek, Sathorn, Bangkok 10120

Tel (662) 679-5120 Fax (662) 6795122

<http://www.bst.co.th>

Specification of Synthetic Latex BST NBL 8503S

Item Name	Specification	Test method
1.Total solid content (%)	44.0-46.0	I-MT1-BL-W155
2.pH (N/A)	8.0-9.0	ASTM D 1417
3.Viscosity (cP)	120 max	ASTM D 1417
4.Coagulum (%wt)	0.010 max	I-MT1-BL-W149
5.Surface tension (Dynes/cm)	20.0-50.0	ASTM D 1417
6.Residual Acrylonitrile (ppm)	40 max	I-MT1-BL-W162