



# LANKO

# 107 WALL PUTTY



Rendering

ACRYLIC PUTTY



Putty

## PACKAGING

- 1.5 kg. bucket.
- 5 kg. bucket.

## STORAGE

- 1 year from date of manufacture if stored in unopened original packaging in dry condition.

## CHARACTERISTICS

- Fast drying.
- White.

## DESCRIPTION

A ready-to-use acrylic putty to fill crack, hole, bubble and rock pockets.

## USES

- Interior and exterior wall.
- Ceiling.
- Substrates : concrete, brick, lightweight block and wood.

## WORK INSTRUCTIONS

### Surface Preparation

1. Surface must be clean, dry, and free of dust, oil, paint.

### Product Preparation

1. Ready-to-use paste. No. water must be added.

### Application

1. Apply with putty knife.
2. Allow a sufficient drying time, use sand paper to remove the remaining from the surface.
3. Apply 2<sup>nd</sup> or more coats and allow drying between each layer for deep cracks or holes.
4. Allow 2 hours curing time before applying covering material.

ISO 9001  
ISO 14001  
OHSAS 18001  
BUREAU VERITAS  
Certification



## PRECAUTIONS

- Temperature range for use : 5°C to 35°C.
- Do not apply to damp substrate.
- Do not add any water or other product.
- Not suitable for movement joint.

## SPECIFICATIONS

<b>Appearance</b>	<b>: White Paste</b>
<b>Main composition</b>	<b>: Synthetic Resins</b>
<b>Drying time before 2<sup>nd</sup> coat (Hours)</b>	<b>: 3-4 Hours</b>
<b>Time before covering (Days)</b>	<b>: 3 Days</b>
<b>Paste density (kg./L.)</b>	<b>: 1.7-1.8 kg./L.</b>
<b>pH</b>	<b>: 8-10</b>

<b>Bonding strength on concrete (MPa)</b>	<b>Evaluation</b>
28 days : 1 mm. thickness	> 0.5
28 days : 3 mm. thickness	> 0.5



094 551 5458



02 651 8003



parexgroup.co.th



e-learning VDO

**ParexGroup Company Limited.** 183 Regent House Building, Rajdamri Road., Lumpini, Bangkok 10330

\*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.

