



LANKO

110 SKIMCOAT DUSTLESS WHITE INTERIOR



Rendering

SKIMCOAT FOR INTERIOR WALL AND CEILING



CHARACTERISTICS

- Thickness: 0.3 to 2 mm.
- Smooth finish.
- Can be exposed or covered.
- Money saving (less paint may be required).
- White.

DESCRIPTION

A ready-mixed powder to mix with water for levelling uneven surface and filling small bubbles.

USES

- Interior wall.
- Ceiling.
- Substrates: concrete and render.

WORK INSTRUCTIONS

Surface Preparation

1. Surface must be clean, dry, and free of dust, oil, paint.
2. New concrete must be dried 3-7 days depend on weather condition before application.
3. Remove seams or edge that is over required thickness.
4. Damp the surface before application.

Product Preparation


1. Mix with power drill one 20 kg. bag with 6.5–7 Litres of clean water until the product is evenly distributed.
2. In case of small quantity, use small paddle to mix at least 3 minutes. Use big paddle to mix for big quantity with the speed not over 500 RPM/minute.
3. Leave to stand for 1-3 minutes.



Interior



Mix with Water



Thickness



Can Spray



Trowel

COVERAGE

- 1.3 kg./sq.m./mm.

PACKAGING

- 20 kg. bag.

STORAGE

- 1 year from date of manufacture if stored in unopened original packaging in dry condition.



Application

1. Apply 1st coat with trowel.
2. One or more coats can be applied to meet the required thickness or texture.
3. Application of many thin layers are the result of quicker drying time than apply one time with thick layer.
4. Allow a sufficient drying time between the coat of 10-45 minutes.
5. Can use sand paper no.380 to polish the surface.
6. Allow 3-7 days before applying covering material.

PRECAUTIONS

- Temperature range for use : 5°C to 35°C.
- Do not apply on gypsum substrate.
- Protect for 24 hours in case of heavy rain or hard sun.
- Not suitable for structural crack subject to movement.
- Do not use on floor.

SPECIFICATIONS

Appearance	: White Powder
Water / Powder ratio	: 34-35 : 100
Drying time before 2d coat (Hours) Time before painting (Days)	: 3-4 Hours : 3 Days
Particle size (mm.)	: 0.04-0.30 mm.
Bulk density (kg./L.)	: 0.8-0.9 kg./L.
Pot life (min.)	: 120 min.

Setting time at 25 °C (min.)	Evaluation
Final Setting time, at + 25 °C (min.)	Maximum at 360 min.
Initial Setting time, at + 25 °C (min.)	Minimum at 240 min.
Bonding strength on concrete (MPa)	Evaluation
28 days : 1 mm. thickness	> 0.5
28 days : 3 mm. thickness	> 0.5



094 551 5458



02 651 8003



parexgroup.co.th



e-learning VDO

ParexGroup Company Limited. 183 Regent House Building, Rajdamri Road., Lumpini, Bangkok 10330

*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.

