



LANKO

112 SKIM AND JOINT FILLER



Rendering

SKIMCOAT AND JOINT FOR INTERIOR WALL AND CEILING



CHARACTERISTICS

- **Thickness: 0.5 to 2 mm.**
- **Smooth finish, after sanding.**
- **Can be exposed or covered.**
- **Quick drying.**
- **Excess product can be stored after mixing.**
- **White.**

DESCRIPTION

A ready-mixed powder to mix with water for levelling uneven surface and filling small bubbles.

USES

- Interior.
- Ceiling and wall.
- All purposes joint.
- Substrates: concrete, render and gypsum.

WORK INSTRUCTIONS

Surface Preparation

1. Surface must be clean, dry, and free of dust, oil, paint.
2. Damage concrete, seams and rock pockets exceeding 3 mm. must be treated prior to application.
3. New concrete must be dried 3-7 days depend on weather condition before application.
4. Damp the surface before application.

Product Preparation

1. Mix with power drill one 20 kg. bag with 8–8.6 Litres of clean water (27-28 % of mortar) until the product is evenly distributed.
2. Use mixing machine mix at low speed not over than 500 RPM.
3. Leave to stand for 1-3 minutes.



Mix with Water



For gypsum



Interior



Can Spray



Trowel

COVERAGE

- 1.3 kg./sq.m./mm.

PACKAGING

- 20 kg. bag.

STORAGE

- 1 year from date of manufacture if stored in unopened original packaging in dry condition.

ISO 9001
ISO 14001
ORSAS 10001
BUREAU VERITAS
Certification



Application

1. Apply 1st coat with trowel.
2. One or more coats can be applied to meet the required thickness or texture.
3. Application of many thin layers are the result of quicker drying time than apply one time with thick layer.
4. Allow a sufficient drying time between the coat of 10-45 minutes.
5. Can use sand paper no.380 to polish the surface.
6. Allow 3-7 days before applying covering material.

PRECAUTIONS

- Temperature range for use : 5°C to 35°C.
- Do not apply on gypsum substrate.
- Protect for 24 hours in case of heavy rain or direct sun.
- Not suitable for structural crack subject to movement.
- Do not use on floor.

SPECIFICATIONS

Appearance	: White powder
Water Powder ratio	: 0.4 - 0.43
Drying time before 2d coat (Hours)	: 3-4 Hours
Time before covering (Days)	: 3 Days
Particle size (mm.)	: 0.04-0.30 mm.
Bulk density (kg./L.)	: 0.8-0.9 kg./L.
Pot life (min.)	: 390 min.

Bonding strength on concrete (Mpa)	Evaluation
28 days : 1 mm. thickness	> 0.5
28 days : 3 mm. thickness	> 1



094 551 5458



02 651 8003



parexgroup.co.th



e-learning VDO

ParexGroup Company Limited. 183 Regent House Building, Rajdamri Road., Lumpini, Bangkok 10330

*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.

