

# 241 FLOOR LIQUID

## Floor & Surface **Protection**

#### LIQUID FLOOR HARDENER





## **COVERAGE**

- On porous surface: 1 Litre / 6 sq.m. • On dense surface: 1 Litre / 12 sq.m.
- **PACKAGING**
- 20 Litres container.
- 200 Litres container.

#### **STORAGE**

• 1 year from date of manufacture if stored in unopened original packaging in dry condition.

## **CHARACTERISTICS**

- · Harden existing surfaces.
- Anti-dust.
- Protection against oil and grease.
- Easy to use.

## **DESCRIPTION**

A floor hardener for protecting and hardening existing concrete.

## **USES**

- Substrates : old and new concrete.
- Porous surfaces.

## **WORK INSTRUCTIONS**

### **Surface Preparation**

- 1. Surface must be clean, dry, and free of dust, oil, paint.
- 2. For fresh concrete, allow a minimum of 14 days curing.

#### **Application**

#### **New concrete**

- 1. For the 1st coat, dilute 1 Litre of LANKO 241 FLOOR LIQUID with 2 Litres of clean water, then apply by brush or spray.
- 2. Allow 24 hours before 2<sup>nd</sup> coat.
- 3. For the 2<sup>nd</sup> coat, dilute 1 Litre of LANKO 241 FLOOR LIQUID with 1 Litre of clean water, then apply by brush or spray.









#### Old concrete, soft stone, masonry

- 1. For the 1st coat, dilute 1 Litre of LANKO 241 FLOOR LIQUID with 3 Litres of clean water, then apply by brush or spray.
- 2. Allow 24 hours before 2<sup>nd</sup> coat.
- 3. For the 2<sup>nd</sup> coat, dilute 1 Litre of LANKO 241 FLOOR LIQUID with 2 Litre of clean water, then apply by brush or spray.
- 4. For the 3rd coat, dilute 1 Litre of LANKO 241 FLOOR LIQUID with 1 Litre of clean water, then apply by brush or spray.

## Curing

- 1. LANKO 241 FLOOR LIQUID can be opened to traffic when surface is completely dry after 24 hours at 21°C.
- 2. Wash the surface with clean water after LANKO 241 FLOOR LIQUID is completely dry.

#### **PRECAUTIONS**

- Temperature range for use : 5°c to 35°c.
- Do not apply on waterproof, bituminous or paint surface.
- · Wear gloves and safety goggles.

#### **SPECIFICATIONS**

**Density** : 1.0-1.1 : 2.5-4.0 Hq Solid content : 2-4 **Viscosity** : 5-10 Open to light traffic (Hours) : 24

Abrasion resistance	Evaluation
Taber abrasion, H22 disk-500g-200 rmp	
7 days	N/A
28 days	N/A





02 651 8003





e-learning VDO

ParexGroup Company Limited. 183 Regent House Building, Rajdamri Road., Lumpini, Bangkok 10330

\*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the lasted version of this document.

