



LANKO

534 REBAR ANCHORING



Repairing
and Grouting

EPOXY ADHESIVE FOR ANCHORING AND REPAIRING



CHARACTERISTICS

- No shrinkage.
- Good workability.
- Protect steel rebar from corrosion.
- Can be applied on dry or slightly damp surface.
- Can be applied on vertical surface.

DESCRIPTION

Dual-component epoxy with high bonding and high tensile strength.

USES


- Rebar anchoring.
- Repair of crack and reshaping of concrete and mortar.
- Tiling.



High bonding



Dual Component



Rebar Anchoring

COVERAGE

- 1.5 kg./sq.m./mm.

PACKAGING

- 1 kg. set (Part A and Part B)
- 2 kg. set (Part A and Part B)

STORAGE

- 1 year from date of manufacture if stored in unopened original packaging in dry condition.

WORK INSTRUCTIONS

Surface Preparation

1. Surface must be clean, dry, and free of dust, oil, paint.

Product Preparation

1. Machine-mix resin and hardener on slow speed until grey paste is obtained.
2. Must be used within 20-30 minutes after mixed.

Application (Rebar anchoring)

1. Drill holes 1-3 mm. wider than the diameter of the rebar.
2. Apply to dry or slightly damp substrate.
3. Spread mixture onto the substrate and place the material.
4. Bonding must be carried out when the adhesive becomes sticky, i.e. between 10-30 minutes, depending on temperature and humidity.



PRECAUTIONS

- Temperature range for use : 5°C to 35°C.
- Avoid prolonged skin contact.
- Wear gloves and safety goggles.

SPECIFICATIONS

pH	:	12-13
Pot Life (min.)	:	30
Viscosity at 25°C (cp)	:	300,000-400,000

Tensile strength ASTM C190-bone (MPa)	Evaluation
1 day	> 4
28 days	> 7

Bonding at 28 Days-Adhesion (MPa)	Evaluation
EN 1542 initial bonding (7 days to concrete)	> 1
EN 1542 initial bonding (28 days to concrete)	> 2



094 551 5458



02 651 8003



parexgroup.co.th



e-learning VDO

ParexGroup Company Limited. 183 Regent House Building, Rajdamri Road., Lumpini, Bangkok 10330

*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.

