



LANKO

761 STEEL



Repairing
and Grouting

CORROSION INHIBITOR



CHARACTERISTICS

- Improve bonding.
- Improve resistance to tension, abrasion and impact.
- Reduce shrinking, cracking and chalking.
- Can be used for smooth substrate.

DESCRIPTION


A corrosion inhibitor with fast concrete penetration.

USES

- Concrete with corroded steel.
- Concrete with insufficiently-coated steel.



Corrosion Protection



Fast Concrete
Penetration

WORK INSTRUCTIONS

Surface Preparation

1. Surface must be clean and without any trace of oil, laitance, curing compound, damaged concrete or paint.
2. Concrete surface must be strong without cracking.
3. Cracking concrete that have dust must be clean before application.
4. Remove any paints on the surface.
5. Clean the surface with high pressure hot water.

Application

1. Apply with a low pressure sprayer, a roller or a brush. Apply with a minimum of 3 or 4 consecutive layers, depending on the porosity of the concrete.
2. After 24 hours, the product will penetrate the concrete and become protection for the steel.
3. Finish the treatment by rinsing the entire surface with clean water, including areas which may have been coated with the LANKO 761 STEEL (railings, windows, door frames, etc.).

PACKAGING

- 20 Litres container.

STORAGE

- 1 year from date of manufacture if stored in unopened original packaging in dry condition.



Compatibility

1. Compatible with all LANKO repair mortars and can be painted over (check the paint manufacturer's technical data sheet).

PRECAUTIONS

- Temperature range for use : 5°C to 35°C.
- Shake the container before use.
- Wear gloves and safety goggles.

SPECIFICATIONS

Bulk Density (kg./L.)	:	1.03
pH	:	7-9



e-learning VDO

ParexGroup Company Limited. 183 Regent House Building, Rajdamri Road., Lumpini, Bangkok 10330

*The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.