

TEST REPORT

No. : XMIN2503000248PL01_EN

Date : 2025-03-19

Page: 1 of 4



CUSTOMER NAME: K.O.H. INTERNATIONAL CO., LTD.
ADDRESS: 45 MOO 1, TUMBON BORNGERN, AMPHUR LADLUMKAEW
PRATHUMTHANEE 12140, THAILAND

Sample Name : POLYESTER PVC MESH SHEET
Product Specification : 250DX250D 24X24 130g/ m²
Material : PVC+POLYESTER
Other Information : IPT68001-2

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : GZMR250300609301
Date of Receipt : 2025-03-10
Testing Period : 2025-03-10 ~ 2025-03-14
Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services Co., Ltd. Xiamen Branch.

Jude Zhao
Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5761588 www.sgsgroup.com.cn
t (86-592) 5761588 sgs.china@sgs.com

TEST REPORT

No. : XMIN2503000248PL01_EN


Date : 2025-03-19

Page: 2 of 4

Summary of Results:

No.	Test Item	Test Method	Result
1	Tensile Test	ISO 1421:2016 Method 1	See Result

Original Sample Photo:



TEST REPORT

No. : XMIN2503000248PL01_EN

Date : 2025-03-19

Page: 3 of 4

Test Item: Tensile Test

Sample Description: Sheet

Test Method: ISO 1421:2016 Method 1

Test Condition:

Specimen width: 50mm

Testing speed: 100mm/min

Grip separation: 100mm


Lab Environmental Condition: (23±2)°C, (50±5)%RH

Test Result:

Test Item	Test Result	
Maximum Force	X direction	857N
	Y direction	873N
Elongation at Break	X direction	21.0%
	Y direction	22.0%

Note: Test specimens were cut from the sample.

Test Photo:




TEST REPORT

No. : XMIN2503000248PL01_EN

Date : 2025-03-19

Page: 4 of 4



Note: The above test project/method was carried out by subcontractors.

*****End of report*****