

## TEST REPORT

No. : XMIN2503000248PL08\_EN

Date : 2025-03-28

Page: 1 of 3



CUSTOMER NAME: K.O.H. INTERNATIONAL CO., LTD.  
ADDRESS: 45 MOO 1, TUMBON BORNGERN, AMPHUR LADLUMKAEW  
PRATHUMTHANEE 12140, THAILAND

Sample Name : POLYESTER PVC MESH SHEET  
Product Specification : 1500DX1500D 11X11 370g/ m<sup>2</sup>  
Material : PVC+POLYESTER  
Other Information : IPT68001-7

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*

SGS Ref. No. : AJFTS25001374R04\_EN  
Date of Receipt : 2025-03-10  
Testing Period : 2025-03-10 ~ 2025-03-27  
Test result(s) : For further details, please refer to the following page(s)  
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for  
SGS-CSTC Standards Technical  
Services Co., Ltd. Xiamen Branch.

Jude Zhao  
Authorized signatory



SGS-CSTC Standards Technical Services Co., Ltd.  
Xiamen Branch Testing Service Materials Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5761588 www.sgsgroup.com.cn  
t (86-592) 5761588 sgs.china@sgs.com

## TEST REPORT

No. : XMIN2503000248PL08\_EN

Date : 2025-03-28

Page: 2 of 3

### Test Conducted

The test was conducted in accordance with JIS L 1091:1999 Testing methods for flammability of textile Method A-1 (45° micro burner method).

### Test specimen

Sample description	Mesh
Color	Grey
Area density	301 g/m <sup>2</sup>
Size of specimen	350 mm × 250 mm

### Conditioning:

Cleansing procedure: None

Prior to testing, the specimens were left in a thermostatic dryer at a temperature of 50±2°C for 24 h, then cooled in a desiccator containing silica gel for 2 h or longer as it is.

If testing is not carried out immediately after conditioning place the conditioned test specimens in a sealed container.

### Test results

Flame application 1 min test

Specimen No.	Warp			Weft		
	1	2	3	1	2	3
After flame time (s)	0	0	0	0	0	0
Afterglow time (s)	0	0	0	0	0	0
Afterflame and afterglow (s)	0	0	0	0	0	0
Damaged area (cm <sup>2</sup> )	8	7	8	5	6	5

## TEST REPORT

No. : XMIN2503000248PL08\_EN

Date : 2025-03-28

Page: 3 of 3

### Classification method for flammability

Division	Heating for 1 min			After 3s from flaming			
	Burned area (cm <sup>2</sup> )	Afterflame time (s)	Afterflame time + afterglow time (s)	Burned length (cm)	Burned area (cm <sup>2</sup> )	Afterflame time (s)	Afterflame time + afterglow time (s)
1	Over 45	Over 3	Over 5	Over 20	Over 45	Over 10	Over 15
2	45 max.	3 max.	5 max.		45 max.	10 max.	15 max.
3	30 max.			20 max.	30 max.	3 max.	5 max.

**Final classification:** [ ] Division 1, [ ] Division 2, [ ☒ ] Division 3.

**Statement:** This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

**Note:** The above test project/method was carried out by subcontractors.

### Photo Appendix:



\*\*\*\*\*End of report\*\*\*\*\*