

TEST REPORT

CLIENT: K.O.H. INTERNATIONAL COMPANY LIMITED
 No.45, VILLAGE 1, BORNGERN SUB-DISTRICT,
 LATLUMKAE0 DISTRICT, PATHUMTHANI 12140

REPORT NUMBER: G 3319/65
 DATE OF RECEIPT: 13/06/22
 DATE OF TEST: 14/06/22-20/06/22
 ISSUE DATE: 20/06/22
 PAGE: 1/2

SAMPLE NUMBER: G 3319/65
 SAMPLE NAMES (AS SPECIFIED BY THE CLIENT): SAFETY NET
 DP/LOT/HEAT NO. : GR22050112
 REFERENCE CODE : IPT65002

SAMPLE DESCRIPTION: -

CLIENT'S REQUIREMENT		G 3319-1/65			CONCLUSION
FLAME PROPAGATION OF TEXTILES AND FILM: NFPA 701: 2019 METHOD 2					
	PERFORMANCE CRITERIA(S)	AFTERFLAME TIME (SECONDS)	FLAME TIME OF DRIPPING (SECONDS)	CHAR LENGTH (mm)	FAIL
FLAMMABILITY (FOLDED SPECIMEN)	- AFTERFLAME TIME < 2 SECONDS				
- TEST SPECIMEN 1	(PER SPECIMEN)	121	50	440	
- TEST SPECIMEN 2	- CHAR LENGTH OF FOLDED SPECIMEN	466	78	660	
- TEST SPECIMEN 3	< 1050 mm	162	70	460	
- TEST SPECIMEN 4	- FLAME TIME OF DRIPPING < 2 SECONDS	450	59	790	
AVERAGE	(PER SPECIMEN)	300	64	588	

REMARK(S):

- THE TEST SPECIMENS WERE NOT LAUNDERED OR DRYCLEANED BEFORE TESTING.
- AFTERFLAME TIME IS THE DURATION OF BURNING OF THE SPECIMEN AFTER IGNITING FLAME HAS BEEN REMOVED.
- TEST APPARATUS : LARGE SCALE VERTICLE FLAMMABILITY TESTER (GOVMARK 701-LX)

AUTHORIZED BY

Pornpimon N.

(MS. PORNPIMON NGAOSAENGTHUM)
 (TEXTILE TESTING LABORATORY MANAGER)

254879

"การปลอมรายงานผลการทดสอบ ไม่ว่าจะเป็นการปลอมทั้งฉบับหรือแต่ส่วนหนึ่งส่วนใด หรือใช้รายงานผลการทดสอบปลอม เป็นความผิดตามประมวลกฎหมายอาญา"

TEST REPORT

REPORT NUMBER: G 3319/65
DATE OF RECEIPT: 13/06/22
DATE OF TEST: 14/06/22-20/06/22
ISSUE DATE: 20/06/22
PAGE: 2/2




FIGURE 1 : G 3319-1/65 (BEFORE TEST)



FIGURE 2 : G 3319-1/65 (AFTER TEST)

“การปลอมรายงานผลการทดสอบ ไม่ว่าจะเป็นการปลอมทั้งฉบับหรือแต่ส่วนหนึ่งส่วนใด หรือใช้รายงานผลการทดสอบปลอม เป็นความผิดตามประมวลกฎหมายอาญา”

This test report refers to the submitted sample(s) for testing/examining/analyzing only. It is not certified for the advertisement or reference of the products/goods. The total or the part of this report may not be reproduced without the written approval from Textile Testing Center, Thailand Textile Institute.