

ที่ สลท 3531/2567

18 กรกฎาคม 2567

เรื่อง รายงานผลทดสอบ/วิเคราะห์

เรียน คุณอลิสา อ่อนอิง

บริษัท เค.โอ.เอช. อินเตอร์เนชั่นแนล จำกัด

45 ม. 1 ต.บ่อเงิน อ.ลาดหลุมแก้ว จ.ปทุมธานี 12140

อ้างถึง แบบคำขอรับบริการทดสอบ/วิเคราะห์ เลขที่ 673335 ลงวันที่ 10 กรกฎาคม 2567

สิ่งที่ส่งมาด้วย รายงานผลทดสอบ/วิเคราะห์ ภาษาอังกฤษ จำนวน 1 ฉบับ

ISIT No. 3552/2024 , Date : July 17, 2024

ตามที่อ้างถึง บริษัท เค.โอ.เอช. อินเตอร์เนชั่นแนล จำกัด ได้ส่งตัวอย่าง Urethane Castor 8" for Scaffolding จำนวน 2 ตัวอย่าง เพื่อให้สถาบันเหล็กฯ ทดสอบแรงกดต่อไป นั้น บัดนี้สถาบันฯ ได้ดำเนินการแล้วเสร็จ ดังรายงานผลทดสอบ/วิเคราะห์ ตามที่ส่งมาด้วย

จึงเรียนมาเพื่อทราบ

ขอแสดงความนับถือ

นายณัฐพล รัตนมาลี

(นายณัฐพล รัตนมาลี)

หัวหน้าทีมวิชาการ

สถาบันเหล็กและเหล็กกล้าแห่งประเทศไทย

ศูนย์ทดสอบ

ต่อ 124, 128

TESTING CENTER

Page 1 / 3

Test/Analysis Report

ISIT No. 3552/2024

July 17, 2024

Request No. : 673335

Date of Request : July 10, 2024

Customer : K.O.H. International Co., Ltd.

45 Moo 1, T. Borngern, A. Ladlumkaew, Pathum Thani 12140

Type of Sample : Urethane Castor 8" for Scaffolding

Method of Test/Analysis : Compression test

Test Date : July 17, 2024

Testing Location : 1st Fl. Bureau of Industrial Sectors Development Building

Test/Analysis Result : The Results are Attached

Checked by 

(Ms.Kotchaphon Mangmesub)

Academic Team

Approved by 

(Mr.Nattapon Ratahamalee)

Head of Academic Team

Tester : 0192

1. The above results are valid exclusively for tested/analysed samples as mentioned in this report.
2. Publication of the results on testing and analysis is prohibited unless written permission is obtained from the governor of ISIT

Attachment : Compression test results

ISIT No. 3552/2024

July 17, 2024

Request No. : 673335

Customer : K.O.H. International Co., Ltd.

Sample : Urethane Castor 8" for Scaffolding (Red)(Model 3) IPT67004


080-L02-00800113/ GR24010283

Operation No. : TC 6719761

Environmental Conditions : Temperature 24.9 °C, Relative Humidity 33 %RH

Tested by : Universal Testing Machine S/N : Q5968, System ID : 5596Q5968

Sample Name	Urethane Castor 8" for Scaffolding (Red)(Model 3) IPT67004/ 080-L02-00800113/ GR24010283
Test items	Result
Maximum load (kgf)	2627.73



Before test



During test



After test

1. The above results are valid exclusively for tested/analysed samples as mentioned in this report.

2. Publication of the results on testing and analysis is prohibited unless written permission is obtained from the governor of ISIT

Attachment : Compression test results (Cont.)

ISIT No. 3552/2024

July 17, 2024

Request No. : 673335

Customer : K.O.H. International Co., Ltd.

Sample : Urethane Castor 8" for Scaffolding (Orange)(Model 3) IPT67005

080-L02-00800114/ GR24020060

Operation No. : TC 6719762

Environmental Conditions : Temperature 24.9 °C, Relative Humidity 33 %RH

Tested by : Universal Testing Machine S/N : Q5968, System ID : 5596Q5968

Sample Name	Urethane Castor 8" for Scaffolding (Orange)(Model 3) IPT67005/ 080-L02-00800114/ GR24020060
Test items	Result
Maximum load (kgf)	2869.35



Before test



During test



After test

1. The above results are valid exclusively for tested/analysed samples as mentioned in this report.

Signature

2. Publication of the results on testing and analysis is prohibited unless written permission is obtained from the governor of ISIT