B110CR

Black

FEATURES

- Higher heat resistance up to 200°C.
- Excellent chemical, solvent and scratch resistance.
- High resolution for 600DPI printers.
- Applicable to a wide range of synthetic materials: PET/PP/PE/PVC films...
- Ricoh's unique coating on the back allows reliable and superior matching qualities with the thermal head.

APPLICATION AREAS



Automotive



Chemical industry



Electronics



Healthcare

GENERAL CONDITIONS

Usage conditions: 5 to 35°C with 30 to 85% of relative humidity.

Storage life: 24 months after slitting day.

Storage conditions: Keep indoor avoiding high temperature (such as beside a heat source), high humidity, direct

sun light.

CERTIFICATIONS / REGISTRATION / DIRECTIVES

- TSCA (Toxic Substances Control Act)
- RoHs
- WEEE
- 2003/11/EC
- 2000/53/EC
- 76/769/EEC
- ISO EN71-3
- REACH







For other directives, please contact us.









RIBBON PROPERTIES

Ink melting point: 97°C

Polyester film thickness: 4.5µm

Friction coefficient: < 0.050



Total ribbon thickness: < 9µm

Tearing resistance: > 200N/mm²

Transmission density: 0.65mini

PRINTING PROPERTIES

Maximum printing speed: 8IPS

	Non coated paper	Coated paper	PET	PP	PE	PVC
Compatibility	×	X	4	4	✓	✓
Image density	-	-	1.83	1.86	2.03	1.72

Note: Smoothness Bekk fo film must be over 2000s.

Image resolution for film:

Minimum size: - For the lines: 0.1mm

- For the characters: 1.0mm

DURABILITY OF PRINTED IMAGE

TESTS	RESULTS	B110CR with standard matt white polyester
Smear + heat (100°C) Smear with cardboard (weight 1kg - 50 back and forwards)	ANSI > B	Engine oil 250
Heat (220°C) Heat gradient 3,6kgF/cm²	No ink on the cotton fabric	Brake fluid 10 Windshieldwasher 250
Scratch 50 back and forwards with a rub tester	ANSI > B	Diesel Unleaded petrol 170
Light Xenon lamp at 650W/m²	ANSI A	IPA 190 Ethanol 50
Water 24 hours in water	ANSI A	Back & forwards until a beginning of erase



