

CP1290 12V 9Ah (20hr) Sealed Lead Acid (SLA) Battery

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.



Battery Construction



Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

General Features

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.
- Case and cover available in both standard and flame retardant ABS
- Valve Regulated Lead Acid (VRLA) battery

Dimensions and Weight

Length(mm / inch)	151 / 5.94
Width(mm / inch)	65 / 2.56
Height(mm / inch)	94 / 3.70
Total Height(mm / inch)	100 / 3.93
Approx. Weight(Kg / lbs)	2.7 / 4.4



Performance Characteristics

Nominal Voltage	12V
Number of cell	6
Design Life	5 years
Nominal Capacity 77°F(25°C)	
20 hour rate (0.45A, 10.5V)	9Ah
10 hour rate (0.86A, 10.5V)	8.6Ah
5 hour rate (1.53A, 10.5V)	7.65Ah
1 hour rate (5.57A, 9.60V)	5.57Ah
Internal Resistance	
Fully Charged battery 77°F (25°C)	14mOhms
Self-Discharge	
3% of capacity declined per month at 20°C(average)	
Operating Temperature Range	
Discharge	-20~60°C
Charge	-10~60°C
Storage	-20~60°C
Max. Discharge Current 77°F (25°C)	135A(5s)
Short Circuit Current	450A
Charge Methods: Constant Voltage Charge 77°F (25°C)	
Cycle use	14.4-14.8V
Maximum charging current	3.6A
Temperature compensation	-30mV/°C
Standby use	13.5-13.8V
Temperature compensation	-20mV/°C









Discharge Constant Power (Watts at 77°F25°C)

End Voltage	1.85V	1.80V	1.75V	1.70V	1.65V	1.60V
10 min	36.5	39.1	42.0	44.0	46.1	48.3
15 min	30.1	31.2	32.3	33.4	34.7	35.9
30 min	15.8	16.2	17.0	17.7	18.0	19.1
60 min	9.97	10.4	10.7	11.0	11.3	11.5
120 min	5.40	5.56	5.69	5.82	5.90	5.95
180 min	4.20	4.35	4.49	4.62	4.75	4.85
300 min	2.89	2.99	3.05	3.10	3.15	3.18
600 min	1.62	1.68	1.71	1.75	1.78	1.80
1200 min	0.853	0.882	0.902	0.907	0.913	0.918

Discharge Constant Current (Amperes at 77°F25°C)

End Voltage	1.85V	1.80V	1.75V	1.70V	1.65V	1.60V
10 min	19.1	20.4	21.9	22.9	24.1	25.2
15 min	14.3	14.9	15.8	16.5	17.3	18.0
30 min	8.09	8.45	8.93	9.35	9.77	10.2
60 min	5.17	5.29	5.37	5.45	5.52	5.57
120 min	2.63	2.72	2.78	2.84	2.89	2.93
180 min	2.12	2.18	2.23	2.27	2.31	2.34
300 min	1.46	1.51	1.53	1.55	1.57	1.58
600 min	0.827	0.841	0.855	0.866	0.877	0.884
1200 min	0.427	0.442	0.451	0.456	0.462	0.466

CP1290 12V 9Ah (20hr) Sealed Lead Acid (SLA) Battery



DENA ENGINEERING CO.,LTD.

185/1 Wongsawang Road, Wongsawang, Bangsue, Bangkok 10800 THAILAND

Tel. 02-587-7780, 02-910-9600 Fax. 02-587-1624 e-mail: dena@dena.co.th www.dena.co.th