


Copper-Bonded Ground Rod (254 micron)



Copper-Bonded ground rod is made by molecularly bonding pure electrolytic copper onto a low carbon, high tensile steel core with exceeding 0.254 mm (254 micron) thick. The material made of 99.9% pure electrolytic copper with high tensile steel. To ensure in safety and quality, it meets UL and IEC standard for grounding and bonding equipments.



Standard Type (UL-Listed)

Code No.	Nominal Diameter (Ø) (in)	Actual Diameter (Ø) (mm)	Length (ft)	Weight (kg)
GRCBU 128	1/2	12.7	8	2.47
GRCBU 1210	1/2	12.7	10	3.08
GRCBU 588	5/8	14.2	8	3.08
GRCBU 5810	5/8	14.2	10	3.80
GRCBU 348	3/4	17.2	8	4.46
GRCBU 3410	3/4	17.2	10	5.58
GRCBU 18	1	23.1	8	8.04
GRCBU 110	1	23.1	10	10.15

Standard Type

Code No.	Nominal Diameter (Ø) (in)	Actual Diameter (Ø) (mm)	Length (ft)	Weight (kg)
GRCBU 124	1/2	12.7	4	1.23
GRCBU 126	1/2	12.7	6	1.85
GRCBU 584	5/8	14.2	4	1.54
GRCBU 586	5/8	14.2	6	2.31
GRCBU 344	3/4	17.2	4	2.23
GRCBU 346	3/4	17.2	6	3.35
GRCBU 14	1	23.1	4	4.30
GRCBU 16	1	23.1	6	6.09



Test Certificate
IEC 62561 Part 2
UL 467



Material
High tensile strength steel
Copper purity > 99.9%



Application
Suitable for disperse current into the earth.


Note : Special Size, Dimeter, Length Copper thickness can be requested.



Copper-Bonded Ground Rod (375 micron)



Copper-Bonded ground rod is made by molecularly bonding pure electrolytic copper onto a low carbon, high tensile steel core with exceeding 0.375 mm (375 micron) thick. The material made of 99.9% pure electrolytic copper with high tensile steel. To ensure in safety and quality, it meets UL and IEC standard for grounding and bonding equipments.



Standard Type

Code No.	Nominal Diameter (Ø) (in)	Actual Diameter (Ø) (mm)	Length (ft)	Weight (kg)
GRCB375 124	1/2	12.9	4	1.12
GRCB375 126	1/2	12.9	6	1.68
GRCB375 128	1/2	12.9	8	2.59
GRCB375 1210	1/2	12.9	10	3.24
GRCB375 584	5/8	14.3	4	1.60
GRCB375 586	5/8	14.3	6	2.24
GRCB375 588	5/8	14.3	8	3.17
GRCB375 5810	5/8	14.3	10	3.97
GRCB375 344	3/4	17.3	4	2.33
GRCB375 346	3/4	17.3	6	3.49
GRCB375 348	3/4	17.3	8	4.72
GRCB375 3410	3/4	17.3	10	5.80
GRCB375 14	1	23.3	4	4.19
GRCB375 16	1	23.3	6	6.29
GRCB375 18	1	23.3	8	8.35
GRCB375 110	1	23.3	10	10.47



Test Certificate
IEC 62561 Part 2
UL 467



Material
High tensile strength steel
Copper purity > 99.9%




Application
Suitable for disperse current into the earth.

Note : Special Size, Dimeter, Length Copper thickness can be requested.

Copper-Bonded Ground Rod (508 micron)



Copper-Bonded ground rod is made by molecularly bonding pure electrolytic copper onto a low carbon, high tensile steel core with exceeding 0.508 mm (508 micron) thick. The material made of 99.9% pure electrolytic copper with high tensile steel. To ensure in safety and quality, it meets UL and IEC standard for grounding and bonding equipments.



Standard Type

Code No.	Nominal Diameter (Ø) (in)	Actual Diameter (Ø) (mm)	Length (ft)	Weight (kg)
GRCB508 124	1/2	13.2	4	1.13
GRCB508 126	1/2	13.2	6	1.78
GRCB508 128	1/2	13.2	8	2.71
GRCB508 1210	1/2	13.2	10	3.39
GRCB508 584	5/8	14.6	4	1.65
GRCB508 586	5/8	14.6	6	2.48
GRCB508 588	5/8	14.6	8	3.30
GRCB508 5810	5/8	14.6	10	4.14
GRCB508 344	3/4	17.6	4	2.38
GRCB508 346	3/4	17.6	6	3.57
GRCB508 348	3/4	17.6	8	4.79
GRCB508 3410	3/4	17.6	10	6.00
GRCB508 14	1	23.6	4	4.26
GRCB508 16	1	23.6	6	6.40
GRCB508 18	1	23.6	8	8.57
GRCB508 110	1	23.6	10	10.74



Test Certificate
IEC 62561 Part 2
UL 467



Material
High tensile strength steel
Copper purity > 99.9%



Application
Suitable for disperse current into the earth.

Note : Special Size, Dimeter, Length Copper thickness can be requested.