

# Technical Data

## Strax (New)



### Product description

Strax (New) is an interior emulsion paint based on special acrylic binder that gives good washability. It is a smooth matt finishing paint that is easy to clean, with good flow and capable of hiding wall imperfection. It also ensures low odour during and after painting.

---

### Recommended use

For use on interior concrete and masonry, also suitable for Jotafibre wall covering system. Not recommended for areas subject to heavy or frequent condensation.

---

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry ( $\mu\text{m}$ )	30	40	35
Film thickness, wet ( $\mu\text{m}$ )	79	105	92
Theoretical spreading rate ( $\text{m}^2/\text{l}$ )	12,6	9,5	10,8

---

### Physical properties

**Colour** As per the colour card and available in Jotun Multicolor tinting system.

**Solids (vol %)\*** 38  $\pm$  2

**Flash point** Nonflammable

**Water resistance** Good

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

The substrate must be sound, clean, dry, free from dust, oil, grease and laitance etc. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

#### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

### Condition during application

Apply at a temperature between 10°C and 35°C. The temperature of the substrate should be minimum 3°C above the dew point of the air. The temperature and the relative humidity should be measured in the vicinity of the substrate.

---

### Application methods

**Spray** Use airless spray or conventional spray

**Brush** Recommended

**Roller** Recommended

Strax (New)

---

## Application data

<b>Mixing ratio (volume)</b>	The paint is ready to use after proper stirring. If thinning is required, water may be added up to a maximum of 5%.
<b>Thinner/Cleaner</b>	Water
<b>Guiding data airless spray</b>	
<b>Pressure at nozzle</b>	140 - 190 kg/cm <sup>2</sup> (2100 psi)
<b>Nozzle tip</b>	0.021" - 0.027"
<b>Spray angle</b>	65° - 80°
<b>Filter</b>	Check to ensure that filters are clean.

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate
- \* Relative humidity 70%

<b>Substrate temperature</b>	<b>10°C</b>	<b>23°C</b>	<b>40°C</b>
<b>Surface dry</b>	2 h	1 h	0.5 h
<b>Through dry</b>	8 h	6 h	4 h
<b>Dry to recoat, minimum <sup>1</sup></b>	4 h	2 h	1 h
<b>Dry to recoat, maximum <sup>2,3</sup></b>			

1. Recommended data given for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied – reference is made to the corresponding system data sheet.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

<b>Interior</b>	
Jotasealer 03 or Jotasealer 07	1 coat
<b>Strax (New)</b>	<b>2 coats</b>

Other systems may be specified, depending on area of use

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

1 litre, 5 litres and 20 litres

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

---

### DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 1 MAY 2008 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED